

## Grip All Solvent Based

Revision: 19/08/2020

Page 1 from 2

### Technical data

Basis	Synthetic rubber
Consistency	Paste
Curing system	Physical drying and crystallisation
Density**	Ca. 1,35 g/ml
Temperature resistance**	-20 °C → 70 °C
Open time (23°C, 55% RV)*	Ca. 5 min.
Application temperature	5 °C → 30 °C

\* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.

### Product description

Grip All Solvent Based is a fibre reinforced, ready to use, solvented construction adhesive based on synthetic rubber. Compatible with most building materials (porous and non-porous).

### Properties

- Fibre reinforced
- Very fast powerful bonding
- Direct application onto one substrate
- Replaces nails and screws
- Suitable for bonding on uneven surfaces.
- Excellent adhesion on a wide range of construction materials both in interior and exterior applications

### Applications

- Suitable for the bonding of decorative materials, skirting boards, gypsum panels in vertical, horizontal and overhead applications.
- Bonding of carpet grippers, edge strips and aluminium and uPVC stair nosing
- Bonding of wall and floor boards, window frames and partitions
- Suitable for solid fixing of materials like wood, synthetic materials, stone, wall tiles, metal on surfaces of concrete, stone, plasterwork, wood, chipboard etc.

### Packaging

Colour: beige

Packaging: 290 ml cartridge

### Shelf life

At least 12 months in unopened packaging in a dry storage place at temperatures between +5 °C and +25 °C.

### Substrates

Substrates: Various porous and non-porous surfaces such as wood, concrete, stone and other materials commonly used in construction. Nature: rigid, clean, dry, free of dust and grease. Porous surfaces such as plaster and fibre cement board should be primed. Surface preparation: No pretreatment required. There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary adhesion test on any substrate.

### Application method

Application method: Apply the adhesive by means of a caulking gun in equal beads or dots on one of the materials that have to be glued. Always apply a bead on the edges of the components and on edges and corners of panels. Press the surfaces immediately together and batten down with a rubber hammer. Support if needed. For the bonding of non-porous or heavy materials, use the transfer method: press components together and release for max. 5 min. Return parts together and batten down with a rubber hammer. Support may be required on a vertical fixing or for heavy components. The bond may be loaded after 24-48h.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

---

## Grip All Solvent Based

---

Revision: 19/08/2020

Page 2 from 2

Cleaning: With Adhesive Cleaner 90A. Cured Grip All Solvent Based can only be removed mechanically.  
Repair: With the same material.

### Health- and Safety Recommendations

Take the usual labour hygiene into account. Use only in well-ventilated areas. Do not smoke. In case of insufficient ventilation it is appropriate to wear respiratory protection. Consult the packaging label for more information.

### Remarks

- The applied pressure and not the duration of the compression will determine the ultimate strength of the bond.
- In case of overhead applications a combination with mechanical fixing is required.
- Do not use as a mirror adhesive.
- Do not use in applications where continuous water immersion is possible.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.